

SMART IMPORT SRL

Quality Certificate EN 10204 3.1

Brand No. : ER70S-6

Cert. No. : QB1421073054

Customer:

Lot No.	Size mm	Weight ton	Chemical Composition(%)											Deposited Metal						X-ray Inspect	Bend Test
			AWS Requirement	C	Si	Mn	P	S	Cr	Ni	V	Mo	Cu	Tensile Strength (Mpa)	Yield Point (Mpa)	Elongation (%)	Impact Value J (-30℃)				
				0.06-0.15	0.80-1.15	1.40-1.85	≤0.025	≤0.035	≤0.5				≤0.5	≥480	≥400	≥22	≥27 (-30℃)				
2104832	0.8		Test Result	0.080	0.890	1.460	0.009	0.012	0.034	0.006	0.001	0.001	0.100	551	459	29	97	95	92	Class 1	Qualified
2104832	1.0		Test Result	0.080	0.890	1.460	0.009	0.012	0.034	0.006	0.001	0.001	0.100	551	459	29	97	95	92	Class 1	Qualified
2104832	1.2		Test Result	0.080	0.890	1.460	0.009	0.012	0.034	0.006	0.001	0.001	0.100	551	459	29	97	95	92	Class 1	Qualified

1.Application standard: AWS A5.18 & GB/T 8110-2008

2.Company approved by ISO9001: 2008/ISO14001: 2004/OHSAS18001: 2007 quality system certificate

3.If there're any quality problems, please propose within 10 days after receipt, and note the delivery date.

4.This delivery quantity is ton

Drafted
document

SMART IMPORT SRL

Certificat de calitate EN 10204 3.1

Tip material: ER70S-6

Nr. certificat: QB1421073054

Client:

Nr. lot	Dime nsiun e (mm)	Greutate (tone)	Compoziție chimică (%)											Metal depus					Inspecție cu raze X	Test de îndoire	
			Cerințe AWS	C	Si	Mn	P	S	Cr	Ni	V	Mo	Cu	Rezistență la tracțiune (MPa)	Limita de curgere (MPa)	Alung ire (%)	Valoarea energiei de impact (J) la -30°C				
				0.06-0.15	0.80-1.15	1.40-1.85	≤0.025	≤0.035	≤0.5			≤0.5	≥480	≥400	≥22	≥27 (-30°C)					
2104832	0.8		Rezultatul testului	0.080	0.890	1.460	0.009	0.012	0.034	0.006	0.001	0.001	0.100	551	459	29	97	95	92	Clasa 1	Admis
2104832	1.0		Rezultatul testului	0.080	0.890	1.460	0.009	0.012	0.034	0.006	0.001	0.001	0.100	551	459	29	97	95	92	Clasa 1	Admis
2104832	1.2		Rezultatul testului	0.080	0.890	1.460	0.009	0.012	0.034	0.006	0.001	0.001	0.100	551	459	29	97	95	92	Clasa 1	Admis

1.Standard aplicabil: AWS A5.18 și GB/T 8110-2008. 2.Compania este certificată conform sistemelor de management al calității ISO 9001:2008, ISO 14001:2004 și OHSAS 18001:2007. 3.Dacă apar probleme de calitate, vă rugăm să le semnați în termen de 10 zile de la primirea mărfii și să menționați data livrării. 4.Cantitatea livrată este exprimată în tone.	Document redactat
--	----------------------------------